Filled $Co_xNi_{4-x}Sb_{12-y}Sn_y$ skutterudites: processing and thermoelectric properties

Jon Mackey
Mechanical Engineering,
University of Akron

Alp Sehirlioglu
Materials Science and Engineering,
Case Western Reserve University

Fred Dynys
NASA Glenn Research Center

NASA Cooperative Agreement: NNX08AB43A
NASA/USRA Contract: 04555-004

System Background

- Skutterudites are based on $CoAs_3$ mineral; first mined in Skotterud, Norway.
- Exhibit a high figure of merit for n-type systems (ZT=1.7).
- Relatively low cost system.
- Introduce disorder on pnictogen ring sites (X).
  - Dominate heat carrying modes are associated with pnictogen vibration.
- Introduce a range of fillers (A) to scatter various phonon wavelengths.
- Tune electronic properties (A,B,X) for optimal thermoelectric power factor .

Crystal Structure

Eilertsen et al. Acta Mater. **60** (2012) 2178-2185.
Chi et al. Phys. Rev. B **86**: 195209 (2012).

Body-centered cubic space group *Im3*

$A_\delta B_4X_{12}$





Systems Investigated

- Ternary systems studied with combination of solidification and powder processing techniques.
- $Ni_4Bi_8Ge_4$
  - Shown below, skutterudite phase not obtained.
- $Ni_4Sb_8Ge_4$
  - Skutterudite phase not obtained.
- $Ni_4Sb_8Sn_4$





Objectives

- Focus on finding a p-type skutterudite with improved ZT.
- Study behavior of the skutterudite $Co_xNi_{4-x}Sb_{12-y}Sn_y$.
  - Grytsiv et. al has reported a $Ni_4Sb_8Sn_4$ skutterudite system.
  - Parameters of study:
    - x= {0,0.5,1,1.5,2}
    - y={3,4,5}
- Samples created from a melt/mill/hot press procedure.



Sy

- Ternary sy
  of solidific
  technique
- $Ni_4Bi_8Ge_4$
  - Show
    obtai
- $Ni_4Sb_8Ge_4$
  - Skutt
- $Ni_4Sb_8Sn_4$

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)
1	0.0	4.0	9.113
2	0.0	5.0	9.128
3	0.5	5.0	9.126
4	1.0	5.0	9.118
5	1.5	5.0	9.123
6	2.0	5.0	9.104
7	2.0	4.0	9.109
8	2.0	3.0	9.087

Objectives

$A_zCo_2Ni_2Sb_8Sn_4$

Sample #	Filler A	Level (z)	Lattice Parameter (Å)
7	N/A	0.0	9.109
9	Ce	0.1	9.108
10	Dy	0.1	9.114
11	Yb	0.05	9.019
12	Yb	0.1	9.111
13	Yb	0.2	9.114

Sy

- Ternary sy
  of solidific
  technique
- $Ni_4Bi_8Ge_4$
  - Show
    obtai
- $Ni_4Sb_8Ge_4$
  - Skutt
- $Ni_4Sb_8Sn_4$

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)
1	0.0	4.0	9.113
2	0.0	5.0	9.128
3	0.5	5.0	9.126
4	1.0	5.0	9.118
5	1.5	5.0	9.123
6	2.0	5.0	9.104
7	2.0	4.0	9.109
8	2.0	3.0	9.087

Objectives

$A_zCo_2Ni_2Sb_8Sn_4$

Sample #	Filler A	Level (z)	Lattice Parameter (Å)
7	N/A	0.0	9.109
9	Ce	0.1	9.108
10	Dy	0.1	9.114
11	Yb	0.05	9.019
12	Yb	0.1	9.111
13	Yb	0.2	9.114

Sy

- Ternary sy
  of solidific
  technique
- $Ni_4Bi_8Ge_4$
  - Show
    obtai
- $Ni_4Sb_8Ge_4$
  - Skutt
- $Ni_4Sb_8Sn_4$

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)
1	0.0	4.0	9.113
2	0.0	5.0	9.128
3	0.5	5.0	9.126
4	1.0	5.0	9.118
5	1.5	5.0	9.123
6	2.0	5.0	9.104
7	2.0	4.0	9.109
8	2.0	3.0	9.087

Objectives

$A_zCo_2Ni_2Sb_8Sn_4$

Sample #	Filler A	Level (z)	Lattice Parameter (Å)
7	N/A	0.0	9.109
9	Ce	0.1	9.108
10	Dy	0.1	9.114
11	Yb	0.05	9.019
12	Yb	0.1	9.111
13	Yb	0.2	9.114

ICP analysis of an ingot

- 2 Hr @ 1100°C (+20,-10°C /min)
- Silica crucible in He atmosphere
- <1% wt loss



	at%	at%	at%	at%
Co	**9.4**	9.1	7.3	9.0
Ni	**15.6**	14.9	13.7	14.6
Sb	**43.7**	42.4	43.7	44.1
Sn	**31.2**	33.5	35.3	32.2
Ca	**0**	2e-4	7e-4	7e-4
Mg	**0**	1e-4	2e-4	2e-4
Na	**0**	3e-3	4e-3	4e-3

EDS map of an ingot









Milling Details

- Planetary mill
  - 550 rpm
  - Ball to powder weight ratio 3.8
  - Ar atmosphere



Milling XRD



*SKD
^ SbSn
o NiSb
$NiSb_2$
= Sn_3Ni_4

Sample 1 $Ni_4Sb_8Sn_4$ Milling



Sample 4 $Co_1Ni_3Sb_7Sn_5$ Milling



Hot Pressed SEM

Sample 1 $Ni_4Sb_8Sn_4$

- NiSb (3.1wt%, 109nm cryst.) precip 1µm.
- SbSn (1.3wt%, 45 nm cryst.) precip 30 µm.



Sample 2 $Ni_4Sb_7Sn_5$

- NiSb (6.8wt%) precip 1µm.
- Ni_3Sn_4 (1.2wt%) precip 30 µm.
- SbSn (1.4wt%) surrounding Ni_3Sn_4.



Sample 4 $Co_1Ni_3Sb_7Sn_5$

- NiSb (3.2wt%) precip 1µm.
- Ni_3Sn_4 (6.5wt%) precip 1µm.



Rietveld Refinement





FIGURE: Eilertsen et al. Acta Mater. **60** (2012) 2178-2185.

Hot Pressed Structure Refinement

Sample #	Skutterudite $A_\delta B_x B'_{4-x} X_{12-y} X'_y$	Lattice (Å)	SKD (wt%)
1	$Sn_{0.2}Co_{0.0}Ni_{4.0}Sb_{8.5}Sn_{4.4}$	9.113	96.65
2	$Sn_{0.3}Co_{0.0}Ni_{4.0}Sb_{7.9}Sn_{5.1}$	9.128	87.38
3	$Sn_{0.3}Co_{0.6}Ni_{3.4}Sb_{7.2}Sn_{4.7}$	9.126	94.97
4	$Sn_{0.3}Co_{1.2}Ni_{2.8}Sb_{8.3}Sn_{5.4}$	9.118	89.25
5	$Sn_{0.3}Co_{1.5}Ni_{2.5}Sb_{7.0}Sn_{4.7}$	9.123	91.33
6	$Sn_{0.3}Co_{2.4}Ni_{1.6}Sb_{9.4}Sn_{5.8}$	9.104	80.08
7	$Sn_{0.3}Co_{2.1}Ni_{1.9}Sb_{9.1}Sn_{3.7}$	9.109	93.64
8	$Sn_{0.2}Co_{2.1}Ni_{1.9}Sb_{9.0}Sn_{2.6}$	9.087	98.20

Pressed $Co_2Ni_2Sb_7Sn_5$

Density 7.64 g/cm^3
99%

Phase	Wt%
$Co_2Ni_2Sb_7Sn_5$	82.6
Ni_3Sn_4	8.7
Sn	6.2



200°C Anneal 72 Hrs

Density 7.25 g/cm^3
95%

Phase	Wt%
$Co_2Ni_2Sb_7Sn_5$	80.0
Ni_3Sn_4	11.9
Sn	7.6



400°C Anneal 72 Hrs

Density 6.75 g/cm^3
88%

Phase	Wt%
$Co_2Ni_2Sb_7Sn_5$	73.6
Ni_3Sn_4	14.7
Sn	10.0



Electrical Hysteresis

Sample 8 $Co_2Ni_2Sb_9Sn_3$





Sample Stability

Sample 7 $Co_2Ni_2Sb_8Sn_4$



Sample 8 $Co_2Ni_2Sb_9Sn_3$



Transport Properties- Unfilled (40°C)

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)	Seebeck Coefficient ($\mu V/K$)	Electrical Resistivity ($\mu Ohm-cm$)	Thermal Conductivity (W/m-K)
1	0.0	4.0	9.113	-40.7	233	4.7
2	0.0	5.0	9.128	-33.4	255	4.1
3	0.5	5.0	9.126	-8.7	560	2.2
4	1.0	5.0	9.118	32.9	784	1.6
5	1.5	5.0	9.123	13.7	449	1.4
6	2.0	5.0	9.104	7.1	233	3.9
7	2.0	4.0	9.109	17.7	540	2.5
8	2.0	3.0	9.087	37.9	2282	1.5

Co (x) Study





Transport Properties- Unfilled (40°C)

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)	Seebeck Coefficient ($\mu V/K$)	Electrical Resistivity ($\mu Ohm-cm$)	Thermal Conductivity (W/m-K)
1	0.0	4.0	9.113	-40.7	233	4.7
2	0.0	5.0	9.128	-33.4	255	4.1
3	0.5	5.0	9.126	-8.7	560	2.2
4	1.0	5.0	9.118	32.9	784	1.6
5	1.5	5.0	9.123	13.7	449	1.4
6	2.0	5.0	9.104	7.1	233	3.9
7	2.0	4.0	9.109	17.7	540	2.5
8	2.0	3.0	9.087	37.9	2282	1.5

Co (x) Study





Transport Properties- Unfilled (40°C)

$Co_xNi_{4-x}Sb_{12-y}Sn_y$

Sample #	Co (x)	Sn (y)	Lattice Parameter (Å)	Seebeck Coefficient ($\mu V/K$)	Electrical Resistivity ($\mu Ohm-cm$)	Thermal Conductivity (W/m-K)
1	0.0	4.0	9.113	-40.7	233	4.7
2	0.0	5.0	9.128	-33.4	255	4.1
3	0.5	5.0	9.126	-8.7	560	2.2
4	1.0	5.0	9.118	32.9	784	1.6
5	1.5	5.0	9.123	13.7	449	1.4
6	2.0	5.0	9.104	7.1	233	3.9
7	2.0	4.0	9.109	17.7	540	2.5
8	2.0	3.0	9.087	37.9	2282	1.5

Sn (y) Study





Transport Properties- Filled (40°C)

$A_zCo_2Ni_2Sb_8Sn_4$

Sample #	Filler A	Level (z)	Lattice Parameter (Å)	Seebeck Coefficient ($\mu V/K$)	Electrical Resistivity ($\mu Ohm-cm$)	Thermal Conductivity (W/m-K)
7	N/A	0.0	9.109	25.3	659	2.5
9	Ce	0.1	9.108	35.1	1036	2.1
10	Dy	0.1	9.114	27.4	681	2.9
11	Yb	0.05	9.019	23.3	618	2.6
12	Yb	0.1	9.111	25.6	592	2.9
13	Yb	0.2	9.114	-	-	-

Filled Properties





Transport Properties- Filled (40°C)

$A_zCo_2Ni_2Sb_8Sn_4$

Sample #	Filler A	Level (z)	Lattice Parameter (Å)	Seebeck Coefficient ($\mu V/K$)	Electrical Resistivity ($\mu Ohm-cm$)	Thermal Conductivity (W/m-K)
7	N/A	0.0	9.109	25.3	659	2.5
9	Ce	0.1	9.108	35.1	1036	2.1
10	Dy	0.1	9.114	27.4	681	2.9
11	Yb	0.05	9.019	23.3	618	2.6
12	Yb	0.1	9.111	25.6	592	2.9
13	Yb	0.2	9.114	-	-	-

Filled Properties





Mobility and Carrier Comparison



This Work

Yb_xCoSb_3: L. Fu et al. Intermetallics (2013)
Ce_xCoSb_3: D. Morelli et al. Phys. Rev. B (1997)
Others: J.-P. Fleurial et al. Proc. XVI ICT (1997)

S.P.B. Modeling

- Applied a single parabolic band model to the system
- Carrier mass (m/me)
  - N-Type: 5.48
  - P-Type: 1.48
- Optimal carrier density
  - N-Type: 2.1E19 cm^{-3}
  - P-Type: 2.7E19 cm^{-3}



Conclusion

- The $Co_xNi_{4-x}Sb_{12-y}Sn_y$ skutterudite can be synthesized from a melt/mill/hot press schedule.
- Both n- and p-type conduction can be achieved by Co doping.
- System exhibits low thermal conductivity, but also low Seebeck coefficient.
- Thermoelectric performance of the system is hindered by large carrier densities and low carrier mobilities.
- Fillers improve Seebeck coefficient, but do not reduce thermal conductivity.



The University of Akron

Case Western Reserve University EST. 1826
think beyond the possible

Acknowledgements

Tom Sabo, Ray Babuder, Ben Kowalski, Clayton Cross, Kerem Sayir

NASA Glenn Research Center

Dr. Sabah Bux, Dr. Jean-Pierre Fleurial

JPL

NASA Cooperative Agreement: NNX08AB43A

NASA/USRA Contract: 04555-004